

# MATERIAL DATA SHEET

KOVAX EUROPE B.V.

Getfertweg 290-4  
7512 BG Enschede  
The Netherlands

Tel: +31 (0) 53 - 434 31 31  
Fax: +31 (0) 53 - 430 49 00

DATE REVISED: January 01, 2008

## I. GENERAL INFORMATION

**PRODUCT: Super-Tack Discs**  
PART#: 764-; 766-; 783-; 786

### CHEMICAL NAME & SYNONYMS:

Grain, Backing, Binding System, Metal Soap, Nylon Pile

### CHEMICAL FAMILY:

N/A

### PROPER DOT SHIPPING NAME:

N/A

### TRADE NAME & SYNONYMS:

Super-Tack Discs

### FORMULA:

N/A

### DOT HAZARD CLASSIFICATION:

Not Restricted

## II. INGREDIENTS

CHEMICAL NAME	%	COMMON NAME	REG.	CAS. #	THRESHOLD LIMIT VALUE (UNITS)	CARCINOGEN
Grain	34	Aluminum Oxide	N	1344-28-1	15mg/m <sup>3</sup> OSHA, 10mg/m <sup>3</sup> ACGIH	N
Backing	29	Paper, Latexed	N			N
Binding System	31	Mixture	N			N
Metal Soap	5	Stealic Acid	N	1592-23-0		N
Nylon Pile	1	Velour	N			N

## III. PHYSICAL DATA

<b>BOILING POINT: (F)</b> N/A	<b>SPECIFIC GRAVITY: (H<sub>2</sub>O = 1)</b> N/A
<b>VAPOR PRESSURE: (mm Hg.)</b> N/A	<b>PERCENT VOLATILE BY VOLUME: (%)</b> N/A
<b>VAPOR DENSITY: (Air = 1)</b> N/A	<b>EVAPORATION RATE: ( = 1)</b> N/A
<b>SOLUBILITY IN WATER:</b> N/A	<b>ph:</b> N/A
<b>APPEARANCE &amp; ODOR:</b> Paper coated with abrasive material	

## IV. FIRE & EXPLOSION HAZARD DATA

<b>FLASH POINT (TEST METHOD):</b> N/A
<b>AUTO IGNITION TEMPERATURE:</b> N/A
<b>LEL:</b> N/A
<b>UEL:</b> N/A
<b>FLAMMABLE LIMITS:</b> N/A
<b>EXTINGUISHING MEDIA:</b> N/A
<b>SPECIAL FIRE FIGHTING PROCEDURES:</b> Use respiratory protection.
<b>UNUSUAL FIRE &amp; EXPLOSION HAZARDS:</b> Backing & resin will burn or decompose.

## V. HEALTH HAZARD DATA

PRODUCT: Super-Tack Discs  
PART# : 764-; 766-; 783-; 786

<b>Threshold Value:</b> N/A	<b>OSHA Threshold Limit Value:</b> N/A	<b>ACGIH Threshold Limit Value:</b> N/A
<b>Carcinogen - NTP Program:</b> N/A	<b>Carcinogen -IARC Program:</b> N/A	
<b>SYMPTOMS OF EXPOSURE:</b> Coughing, shortness of breath, chronic dust may effect breathing capacity. May cause skin abrasion, eye irritation. <b>Medical Conditions Aggravated by Exposure:</b> N/A <b>Primary Routes of Entry:</b> Inhalation, Ingestion, Skin, Eye <b>EMERGENCY FIRST AID:</b> INHALATION: Remove to fresh air, apply artificial respiration as needed. Obtain first aid or medical assistance. INGESTION: Obtain first aid or medical assistance if needed. SKIN: Obtain first aid or medical assistance if needed. EYE: Wash with large amounts of water obtain first aid or medical assistance if needed.		

## VI. REACTIVITY DATA

<b>STABILITY:</b> Stable	<b>CONDITIONS TO AVOID:</b> N/A
<b>INCOMPATIBILITY:</b> N/A	<b>MATERIALS TO AVOID:</b> N/A
<b>HAZARDOUS POLYMERIZATION:</b> Will not occur.	<b>CONDITIONS TO AVOID:</b> N/A
<b>HAZARDOUS DECOMPOSITION PRODUCTS:</b> In use dust and decomposing resin system fumes are generated.	

## VII. ENVIRONMENTAL PROTECTION PROCEDURE

<b>SPILL RESPONSE:</b> Normal clean up procedure.
<b>WASTE DISPOSAL METHOD:</b> Standard landfill methods consistant with applicable federal, state & local laws.

## VIII. SPECIAL PROTECTION INFORMATION

<b>EYE PROTECTION:</b> Recommended	<b>SKIN PROTECTION:</b> Gloves if desired.
<b>RESPIRATORY PROTECTION:</b> As needed, approved dust respirator	<b>VENTILATION RECOMMENDED:</b> LOCAL: recommended MECHANICAL: recommended OTHER: NAIF
<b>OTHER PROTECTION:</b> Measure to be taken during repair and maintenance of contaminated equipment that has been contact with this material: SEE Section VI, VII, VIII.	

## IX. SPECIAL PRECAUTIONS

<b>HYGENIC PRACTICES IN HANDLING &amp; STORAGE:</b> Handle with adequate ventilation.
<b>PRECAUTIONS FOR REPAIR &amp; MAINTENANCE OF CONTAMINATED EQUIPMENT:</b> N/A
<b>OTHER PRECAUTIONS:</b> N/A

## X. PRODUCT APPLICATION

**PRODUCT: Super-Tack Discs**

**PART# : 764-; 766-; 783-; 786**

### **DISC 152 MM, 7 HOLES**

**GRIT:** P60-P600

**FIELD OF APPLICATION:** Automotive, industry

**PRODUCT APPLICATION:** Can be applied throughout the entire sanding process, from the removal of the old paint/oxidation up to spraying the new paint.

**USAGE INSTRUCTION:**

- Remove paint and/or oxidation (+/- P60 - +/-P150)
- Sand the putty (+/- P60 - +/-P150)
- Reduce sanding scratches (+/- P150 - +/- P320)
- Bring on the primer
- Further reduce sanding scratches (+/- P320-P360)
- Scuff the old paint, sand the sides and the filler (+/- P500)
- Bring on the new paint
- For the following steps of the sanding process, we advise the products as mentioned under remark

**REMARK:** For clear coat preparation, we advise our Yellow film products (P800-P1500). Use our Tolex and Buflex range for the removal of final imperfections and polishing purposes and finish the sanding process with polishing the clear coat with our coarse and ultrafine polish products.

### **DISC 203 MM, 8 HOLES**

**GRIT:** P40-P360

**FIELD OF APPLICATION:** Yacht building, Industry (e.g. trucks)

**PRODUCT APPLICATION:** For sanding large surfaces. Only for the coarser sanding work.

The information contained herein is based on data considered accurate. However, no warranty is expressed or implied regarding the accuracy of these data or the results to be obtained from the use thereof.

Vendor assumes no responsibility for injury to vendee or third persons proximately caused material if reasonable safety procedures are not adhered to as stipulated in the data sheet. Additionally, vendor assumes no responsibility for injury to vendee or third persons proximately caused by abnormal use of the material even if reasonable safety procedures are followed. Furthermore, vendee assumes the risk in his use of the material.